

Group II

Kv @ 40°C	Kv @ 100°C	VI	Colour ASTM D1500
65N			
9.0 - 10.0 cSt	2.0 - 2.7 cSt	Min. ≥ 95	≤ 0.5
100N			
18 - 23 cSt	3.9 - 4.6 cSt	Min. ≥ 100	≤ 0.5
150N			
28 - 35 cSt	4.7 - 5.6 cSt	Min. ≥ 100	≤ 0.5
220N			
41 - 47 cSt	5.9 - 6.7 cSt	Min. ≥ 95	≤ 0.5
500N			
90 - 105 cSt	10 - 12 cSt	Min. ≥ 95	≤ 0.5
600N			
96 - 110 cSt	11.6 - 12.9 cSt	Min. ≥ 95	≤ 0.5

Typical properties shown in table. Please request product PDS for specific information.